

## Technical Data Sheet ---M395

Polyether-----based TPU (Thermoplastic Polyurethane)

### 1. Feathers:

Excellent Processing Properties, Good Fast Setting Cost Efficiency, No Migration, Excellent Transparency.

### 2. Applications

Phone & Pad Cover, Footwear, Wheel & Castor, Seals, Wire & Cable, Ear tags etc

### 3. Properties

Properties	Standard	Unit	Value
<b>Physical Properties</b>			
Density	ASTM D792	g/cm	1.21
Hardness	ASTM D2240	Shore A	95
	ASTM D2240	Shore D	/
<b>Mechanical Properties</b>			
100% Modulus	ASTM D412	Mpa	13
300% Modulus	ASTM D412	Mpa	26
Tensile Strength	ASTM D412	Mpa	39
Tear Strength	ASTM D624	KN/m	125
Elongation at Break	ASTM D412	%	450
TG	DCS	° C	-40

Note: The above values are shown as typical values should not be used as specifications.

**4. Package:** 25kg/bag.

### 5. Processing Guide

For optimum results, previous drying of the product during 3-4 hours at 100-110°C is available, in a hot air circulatory, vacuum or desiccant-air dryer.

### 6. Environmental & Healthy & Safety

Take MSDS for reference.